



KEMIKO STONE TONE SEALER

Low Viscosity Acrylic Urethane

Description

KEMIKO Stone Tone Sealer is a waterborne, water viscosity, single component, superior coalescing acrylic urethane polymer product that offers ultra-low VOC, is very user friendly, stain resistant, and cures to a hard resilient film. Kemiko Stone Tone Sealer is supplied in clear gloss and clear satin sheen, is non-yellowing when subjected to exterior atmospheric exposure.

Applications

KEMIKO Stone Tone Sealer is applied to properly prepared concrete, plaster, wood, and metals and utilized as a resilient protective finish coat over faux finishes, Kemiko Chemical Stains, Rembrandt Polymer Stains, and other topcoats for added UV resistance, abrasion resistance and washability. Typical applications include commercial and residential cement floors, theme parks, hospitals, showroom floors, schools, shopping malls, and many other floor surfaces requiring additional protection. Excellent replacement product for high VOC lacquers, acrylics, and varnishes, which cures fast to a hard resilient film with excellent flow properties.

Performance

VOC – <50 g/l *Meets Final SCAQMD Rule 1113 (2008)*

Pencil Hardness – **2H** *ASTM D-3363*

Dry Tape Adhesion – **5A-5B** *ASTM D-3359*

Stain Resistance – *Mustard, Catsup, Soft Drinks, Coffee, Grease & Grime, Fruit Juices, Commercial Cleaners.*

Excellent Leveling & Flow – *Brush, Roll & Spray Applications*

AUTHORIZED DISTRIBUTOR

COHILLS BUILDING SPECIALTIES, INC.

3825 E. ANNE STREET – PHOENIX, AZ 85040

TEL: (602) 266-0462 WEB: www.cohills.com

Physical Characteristics

Volume Solids:	30%
Weight Per Gallon:	9.5 lbs.
Packaging:	1s, 5 ^s , 55 ^s
FlashPoint:	>200°F.
Gloss:	High Gloss (46-C) – Satin Gloss (46-CF)
Dry Time:	@70°F. 50% RH, 30-minutes to touch 1-hour to recoat – foot traffic 4-hours Heavy traffic in 24-hours, Full cure in 48-hours (washability)
Film Thickness:	3-4 mils wet to achieve –1.0-1.5 mils dry. DO NOT EXCEED RECOMMENDED FILM THICKNESS – AIR ENTRAPMENT OR FOAMING MAY OCCUR.
Coverage:	300-400 square feet per gallon – per coat
Thinning:	None required. Use mild soap and tap water for cleanup
Primers:	Typically used as clear sealer on bare cement/plaster, wood and other composite surfaces. Exterior carbon steel should be properly prime and base coated or use Sta-Crete SS1600 Series Epoxy or SS3700 Series Epoxy, ZRC Zinc Primers.

Surface Preparation

Concrete – All visible oil, grease, sludge, and any other contaminants shall be removed prior to any abrasive surface preparation, acid etching and water washing. Surface shall be cured, dry and free from alkali stain and laitance. Blas-Trac is preferred for long term adhesion and non-slip surface.

Metals – All visible oil, grease, sludge, and any other contaminants shall be removed prior to any abrasive surface preparation. Prepare carbon steel in accordance with SSPC-SP6 and achieve 1-2 mil surface profile. Small surfaces may be prepared in accordance with SSPC-SP2 and SSPC-SP3 followed by SSPC-SP1.

Wood – Surface must be completely dry, free of any contaminants, mildew and organic matter.

Existing Coatings – Wash off any chalk, remove all visible grease, oil, dirt or any other deleterious matter. Spot prime surfaces prior to full application coat.

Application Methods

Brush – Use top-quality nylon bristle brush for best film properties.

Roller – Lambswool or similar cover with phenolic core, ¼ - ½ inch nap thickness.

Spray – Commercial conventional air spray or airless spray equipment utilizing spray gun tip size between .013”-.015”. Adjust pressure for proper atomization.

Environment – Apply between 50°F. – 100°F. and 5°F. above dewpoint.

Safety – Areas such as pool decks, sloped driveways, or other surfaces subjected to water may become slippery if coated with KEMIKO Clear Acrylic Urethane. If you must seal these surfaces, keep the sealer film build-up to a minimum. In severe cases a non-slip material such as fine glass beads, washed silica sand and other aggregates may be broadcasted between coating applications.

Contact EPMAR for any additional application information.

WARRANTY

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.

1/26/2004